



5700GP FIBERGLASS BODY FILLER

ET5700GP-300, 3kg green ET5700GP-100, 1kg green

Product	2K polyester glassfiber reinforced body filler for leveling and bridging of cracks, small holes and rusted through areas in automotive, industrial and marine industries.
Substrates	Good adhesion on iron, steel, aluminum, zinc and GRP.
Surface Preparation	Clean, flatten, derust and degrease the surface.
Application Conditions	From 10° C
Mixing	2-3% with hardener
Specific weight	1.60 kg/l
Pot Life	4-5 min at 20°C
Number of layers	Can be applied in several thin layers.
Drying	20-25 min at 20°C
Drying with IR lamps	8-10 min
Sanding	Dry sanding only P80-P120
Shelf life	12 months

Technical Data Sheet etalon-refinish.com